

GYPSUM S-350

S-350 is the most popular concrete capping products of Capstone Series. S-350 provides the best balance of working ability and strength performance for concrete capping.

The water and gypsum ratio for S-350 is recommended to be 23-24%. After simply mixing with water, the gypsum can be used immediately and will fully harden in approximately 30 minutes. with strength reaching over 350 kgf/cm², equals to 5000psi.



GYPSUM S-350

SPECIFICATION

- Cylinder Compressive Strength: **350 kgf/cm² (5000 psi)**
- Maximum Thickness (Average Thickness of Cap): **6 mm**
- Maximum Thickness (Any Part of Cap): **8 mm**

STANDARDS

- According to the regulations of **U.S. ASTM C617 standard**
- Conforms to **ASTM C617 5.3.1 standard**

FEATURES

- Gypsum capping is the most convenient, efficient, rapid, and safest capping method
- Uses **100% pure gypsum** (no extra filler)
- High strength capping gypsum
- Every delivered lot is under strict quality control

ORDERING CODE

- High strength gypsum capping material